

TECHNICAL SPECIFICATIONS OF LEATHER

MANUFACTURER	CURTIDOS MARTINEZ LEAL, S.L.U.
ADDRESS	Poligono Industrial de Lorca. Parcela J-3. 30800 – LORCA (MURCIA) SPAIN.
TELEFONO/EMAIL	00 34 968 476012 / cml@curtidosmartinezleal.es
CONTACT	Jose R. Martínez
NAME OF ARTICLE	POLO GARDA WHITE 1.7/1.9 mm
ARTICLE DESCRIPTION	Bovine Split with Poliurethane coating
ORIGIN	European
THICKNESS	1.7/1.9 mm (tolerance +/- 0.1 mm)
TANNING	Chrome/synthetic
STAMPED	GARDA
FINISHED	Poliurethane coating FILM POLO
SIZE OF PIECE	16-20 sq.ft. / piece

THECNICAL SPECIFICATIONS OF LEATHER

Test		Standard (recomended)	Typical performance
Abrasion Resistance(UNE ISO 12947)		3 (scale 1 to 5)	3-4
Continuos Flexion resistance (ISO 4643)		80.000 flex.	95.000
Stretght Resistance(UNE 59-005-82)		15 Nw/mm ²	17.7 Nw/mm ²
Tear Resistance (UNE EN-ISO 59-024-83)		Min. 160 Nw	182 Nw
Light Fastness(UNE EN-ISO 105:B02-2014)		5 (scale 1 to 6)	5
Permeability (UNE-EN ISO 20344)		6 mg/cm ² *hr	6.8 mg/cm ² *hr
pH value (UNE EN-ISO-4045:1999)		≥ 3.5	3.7

CURTIDOS MARTINEZ LEAL, S.L.U.

Polígono industrial de Lorca – Parcela J.3 – Aptdo. 444 – 30800 LORCA (Murcia) – (ESPAÑA)
 TELF. 968 476 012 – fax 968 466 312 e-mail: cml@curtidosmartinezleal.es